

**LOCTITE® 554™**

July 2012

**PRODUCT DESCRIPTION**

LOCTITE® 554™ provides the following product characteristics:

|                             |                                    |
|-----------------------------|------------------------------------|
| <b>Technology</b>           | Acrylic                            |
| <b>Chemical Type</b>        | Methacrylate ester                 |
| <b>Appearance (uncured)</b> | Red liquid <sup>LMS</sup>          |
| <b>Fluorescence</b>         | Negative                           |
| <b>Components</b>           | One component - requires no mixing |
| <b>Viscosity</b>            | Medium                             |
| <b>Cure</b>                 | Anaerobic                          |
| <b>Secondary Cure</b>       | Activator                          |
| <b>Application</b>          | Thread sealing                     |

LOCTITE® 554™ provides maximum solvent resistance on threaded fittings and pipe up to 50 mm (2 in.) in diameter. It is recommended for refrigeration systems and service with strong chemicals. The sealant is used in place of specialty non-hardening compounds, litharge, glycerine, and sealing tape. **This product is not for slip fitted tube joints.** This product is typically used in applications up to 149 °C. Typical applications include metal and fiber plants, chemical processing, paper processing plants, waste treatment facilities and textile industries.

**TYPICAL PROPERTIES OF UNCURED MATERIAL**

|   |                               |
|---|-------------------------------|
| Specific Gravity @ 25 °C                        | 1.02                          |
| Flash Point - See SDS                           |                               |
| Viscosity, Brookfield - RVT, 25 °C, mPa·s (cP): |                               |
| Spindle 3, speed 20 rpm,                        | 1,500 to 3,500 <sup>LMS</sup> |

**TYPICAL PROPERTIES OF CURED MATERIAL****Physical Properties:**

|  |     |
|--|-----|
| Coefficient of Thermal Expansion, ISO 11359-2, K <sup>-1</sup> | 0.1 |
| Coefficient of Thermal Conductivity, ISO 8302, W/(m·K)         | 0.1 |
| Specific Heat, kJ/(kg·K)                                       | 0.3 |

**TYPICAL PERFORMANCE OF CURED MATERIAL****Adhesive Properties**

Cured for 24 hours @ 22 °C

Prevail Torque, ISO 10964:

|   |          |                      |
|---|----------|----------------------|
| 3/8 x 24 steel nuts (grade 2) and bolts (grade 5) | N·m      | ≥10.8 <sup>LMS</sup> |
|   | (lb.in.) | (≥95.5)              |

Cured for 72 hours @ 22 °C

Breakaway Torque, ISO 10964:

|   |          |       |
|---|----------|-------|
| 3/8 x 24 steel nuts (grade 2) and bolts (grade 5) | N·m      | 27.2  |
|   | (lb.in.) | (240) |

Prevail Torque, ISO 10964:

|   |          |       |
|---|----------|-------|
| 3/8 x 24 steel nuts (grade 2) and bolts (grade 5) | N·m      | 23.8  |
|   | (lb.in.) | (210) |

**GENERAL INFORMATION**

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

**Directions for use:****For Assembly**

1. For best results, clean all surfaces (external and internal) with a LOCTITE® cleaning solvent and allow to dry.
2. If the material is an inactive metal or the cure speed is too slow, spray all threads with Activator 7471™ or 7649™ and allow to dry.
3. Apply a 360° bead of product to the leading threads of the male fitting, leaving the first thread free. Force the material into the threads to thoroughly fill the voids. For bigger threads and voids, adjust product amount accordingly and apply a 360° bead of product on the female threads also.
4. Using compliant practices, assemble and wrench tighten fittings in accordance with manufacturers recommendations.
5. Properly tightened fittings will seal instantly to moderate pressures. For maximum pressure resistance and solvent resistance allow the product to cure a minimum of 24 hours.

**For Disassembly**

1. Remove with standard hand tools.
2. In rare instances where hand tools do not work because of excessive engagement length, apply localized heat to nut or bolt to approximately 250 °C. Disassemble while hot.

## For Cleanup

1. Cured product can be removed with a combination of soaking in a Loctite solvent and mechanical abrasion such as a wire brush.

## Loctite Material Specification<sup>LMS</sup>

LMS dated September 1, 1995. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

## Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

## Conversions

(°C x 1.8) + 32 = °F  
 kV/mm x 25.4 = V/mil  
 mm / 25.4 = inches  
 µm / 25.4 = mil  
 N x 0.225 = lb  
 N/mm x 5.71 = lb/in  
 N/mm² x 145 = psi  
 MPa x 145 = psi  
 N·m x 8.851 = lb·in  
 N·m x 0.738 = lb·ft  
 N·mm x 0.142 = oz·in  
 mPa·s = cP

## Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly

recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

## Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

## Reference 1.3