

LOCTITE[®] PC 7255[™]

Known as LOCTITE[®] Nordbak[®] Sprayable Ceramic 7255[™]
October 2016

PRODUCT DESCRIPTION

LOCTITE[®] PC 7255[™] provides the following product characteristics:

Technology	Epoxy
Chemical Type	Epoxy
Appearance (Resin)	Green or grey liquid ^{LMS}
Appearance (Hardener)	Blue or grey liquid ^{LMS}
Appearance (Mixture)	Brilliant green or grey liquid
Components	Two part - Resin & Hardener
Mix Ratio, (by volume)	100 : 50
Resin : Hardener	
Mix Ratio, by weight -	100 : 50
Resin : Hardener	
Cure	Room temperature cure after mixing
Application	Coating
Product Benefits	<ul style="list-style-type: none"> • Smooth sprayable consistency • Gloss finish to reduce friction and turbulence • Excellent adhesion
Specific Application	<ul style="list-style-type: none"> • Resurfacing and repairing of worn or corroded metal parts • Protecting metal surfaces against abrasive and corrosive agents

LOCTITE[®] PC 7255[™] sprayable ceramic is a solvent-free ceramic filled two part epoxy coating. It is designed to protect metal surfaces against abrasive and corrosive agents. It can be used as smooth, protective coating on metal surfaces or as a low friction top coat over LOCTITE[®] Nordbak[®] wear resistant compounds. Typical applications are repairing and protecting of heat exchangers, condensers, lining tanks, chutes, valve bodies or pump impellers and housings.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Resin

Specific Gravity @ 25 °C	1.5
Viscosity, Brookfield - DVT,25°C,mPa·s (cP):	
Spindle 7., speed 100 rpm	12,000
Viscosity, Plate to Plate mPa·s (cP):	
Temperature: 25 °C, Shear Rate: 0.3 s ⁻¹	70,000 to 120,000 ^{LMS}
Temperature: 25 °C, Shear Rate: 40 s ⁻¹	3,500 to 6,500 ^{LMS}

Hardener

Specific Gravity @ 25 °C	1.5
Viscosity, Brookfield - DVT,25°C,mPa·s (cP):	
Spindle 7., speed 100 rpm	2,700
Viscosity, Plate to Plate mPa·s (cP):	
Temperature: 25 °C, Shear Rate: 0.3 s ⁻¹	12,000 to 31,000 ^{LMS}
Temperature: 25 °C, Shear Rate: 40 s ⁻¹	700 to 2,000 ^{LMS}

Mixed

Specific Gravity @ 25 °C	1.5
Viscosity, Brookfield - DVT,25°C,mPa·s (cP):	
Spindle 7., speed 100 rpm	5,000
Vertical Sag Resistance, 25 °C, ISO 16862, µm:	700
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Pot life (200 g mass), ISO 9514, minutes:	40 to 70 ^{LMS}
Recoat time, @ 25 °C, hours:	1 to 3

Surface Drying Time - ISO 1517

@ 15 °C, hours	7
@ 22 °C, hours	4
@ 35 °C, minutes	90
@ 45 °C, minutes	70

TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 7 days @ 22 °C

Physical Properties:

Glass Transition Temperature , °C:	
(Tg) by TMA ISO 11359-2	63
Elongation, at break, ISO 527-2, %	1.4
Shore Hardness, ISO 868, Durometer D	86
Tensile Strength, ISO 527-2	N/mm ² 47
	(psi) (6,815)
Tensile Modulus, ISO 527-2	N/mm ² 5,841
	(psi) (846,945)
Compressive Strength, ISO 604	N/mm ² 106
	(psi) (15,400)
Compressive Modulus, ISO 604	N/mm ² 3,260
	(psi) (472,700)

Electrical Properties:

Dielectric Strength, IEC 60243-1, kV/mm	13
---	----

TYPICAL PERFORMANCE OF CURED MATERIAL

Cured for 7 days @ 22 °C

Tensile Lap Shear Strength, :

Mild Steel (grit blasted)	N/mm ²	31
	(psi)	(4,500)

Taber Wear Resistance, Weight Lost, mg:

Wheels H 18, 1 Kg load, 1,000 cycles	45
--------------------------------------	----

Cathodic Disbondment, Penetration, mm:

(ASTM G 95, 90 day test)	0
--------------------------	---

Dry Service Temperature Resistance, °C

(CSA-Z245.20-06/CSA-Z245.21-06 Rating 1)	110
--	-----

Wet Service Temperature Resistance, °C

(CSA-Z245.20-06/CSA-Z245.21-06 Rating 1)	90
--	----

Note to CSA standard: After storage in hot air or water for 28 days at the temperature indicated the coating applied on a metal panel, Rating 1, cannot be removed cleanly.

TYPICAL ENVIRONMENTAL RESISTANCE

Cured for 7 days @ 22 °C

Chemical Resistance

Tables below show chemical resistance @ 22°C. Tested on product specimens, immersed up to 5,000 hours @ 22°C in fluids indicated.

Acids

10 % hydrochloric	Continuous long term immersion
36 % hydrochloric	Continuous long term immersion
10 % sulphuric	Continuous long term immersion
10 % nitric	Short term or intermittent immersion
5 % phosphoric	Continuous long term immersion

Alkalies

40 % sodium hydroxide	Continuous long term immersion
25 % ammonium hydroxide	Continuous long term immersion
36 % ammonium sulphate	Continuous long term immersion
30 % hydrogen peroxide	Spill, splash with immediate cleanup

Solvents

Deionized Water	Continuous long term immersion
10% Salt Water	Continuous long term immersion
Methanol	Spill, splash with immediate cleanup
% Methyl ethyl ketone (MEK)	Spill, splash with immediate cleanup
Xylene	Spill, splash with immediate cleanup

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions For Use:**Surface Preparation**

Proper surface preparation is critical to the long-term performance of this product. The exact requirements vary with the severity of the application, expected service life, and

initial substrate conditions.

- Remove dirt, oil, grease etc with a suitable cleaner, e.g. high pressure water cleaning system using LOCTITE® 7840™ or LOCTITE® Natural Blue® cleaner/degreaser.
- All skip welds, weld splatter, buckshot, and other surface roughness must be ground down and smoothed; undercuts and pinholes must be ground smooth and filled. All projections, sharp edges, high points and fillets must be ground smooth to a radius of at least 3mm and all corners must be likewise rounded to maximize product performance.
- Blast all surfaces to be coated with a sharp edged angular grit to a depth of profile of 75 to 100 microns, and a degree of cleanliness of Near White Metal (SIS SA 2½ /SSPC-SP 10). For immersion service, a degree of cleanliness of White Metal (SIS SA 3/SSPC-SP 5) is required.
- After blasting, the metal surface should be cleaned with a residue-free cleaner or solvent to remove dust and contaminants. Clean, dry compressed air may also be used to remove dust and contaminants. The surface should be coated before any new oxidation occurs.
- Metal that has been in contact with salt solutions, e.g. seawater, should be grit blasted and high-pressure water blasted, left for 24 hours to allow any salts in the metal to sweat to the surface. A test for chloride contamination should be performed. The procedure should be repeated until chloride concentration on the surface is below 40 ppm.

Application:

- Film thickness per coat: 250 microns (8 mils). Minimum of 2 coats is recommended to avoid any pin holes. Layering of two different colors may be used as a wear indicator for re-application. In this case LOCTITE PC 7255 green should be applied as a first layer
- Multiple coat application may be carried out within the recoat time. If this time has elapsed, light abrasive blasting is required, followed by a solvent wash to remove any abrasive residues
- Apply material to prepared surface by first forcing a thin layer deep into the texture of the substrate
- Then Immediately build up to the desired finished thickness
- For Cartridge system:
 - Pre-heat cartridges to 50°C and maintain this temperature until spraying.
 - Set product pressure to approximately 2 bar (30 psi) and air pressure to approximately 5 bar (70 psi)
 - Place nozzle in a perpendicular position to the substrate with a distance from nozzle to substrate about 30 cm.

Coverage rate

To achieve a 250 microns (8 mils) thickness, the coverage rate will be 2.7 m² (ft²) for 1 kg (lb), excluding overthicknesses, repairs, etc

Inspection

- Visually inspect for pinholes and misses just after application.
- Once the coating has cured, repeat visual inspection to confirm freedom from pinholes, misses and mechanical damages.
- Control thickness of the coating, especially in the critical points.
- Perform a test with a holiday detector to confirm coating continuity.

Repairs

Any misses, pinholes, low thickness areas found in the coating should be repaired by lightly abrading, cleaning and applying further product.

Clean-up

1. Immediately after use clean tools with suitable cleaner, e.g. TEROSON® PU 8550 or BONDERITE® C-MC 21130. Once cured, the material can only be removed mechanically.

Color

Color variation is possible between the batches and will not affect the performance of the product

LOCTITE® PC 7255™ is available in different colors

Loctite Material Specification^{LMS}

LMS dated February 19, 2009 (Resin) and LMS dated December 13, 2008 (Hardener). Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Loctite Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.8