



## Technical Data Sheet

# DOWSIL™ 789 Silicone Weatherproofing Sealant

Neutral, one-part silicone sealant

### Features & Benefits

- Easy of use – all temperature gunability
- Primerless adhesion – upon curing will form a strong bond to most common building components without the use of a primer
- Long-life reliability – cured sealant stays elastomeric from -50°C to 150°C without hardening, cracking or becoming brittle under normal weather conditions
- Low Modulus – with extension/compression capability up to ±50% of original joint width
- Excellent weatherability, virtually unaffected by sunlight, rain, snow, ozone
- Ease of application – ready to use as supplied

### Composition

- One-part, neutral-cure, RTV silicone sealant

### Applications

- DOWSIL™ 789 Silicone Weatherproofing Sealant is a specified, premium performance weather sealing product specifically designed for general glazing and weather sealing in curtain wall and building facades.

### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test <sup>1</sup>	Property <sup>2</sup>	Unit	Result
<b>Uncured – As Tested at 50% RH and 23°C (73°F)</b>			
ASTM D2202	Flow (sag or slump)	inches (mm)	0
	Working Time	minutes	15–30
ASTM C 679	Tack-free Time, 77°F, 50% RH	minutes	< 80
	Curing Time at 77°F (25°C) and 50% RH	days	7–14
<b>As Cured – After 21 days at 50% RH and 77°F (25°C)</b>			
ASTM D 2240	Durometer Hardness, Shore A	points	28
ASTM C 412	Ultimate Tensile Strength	kg/cm <sup>2</sup>	16
	Ultimate Elongation	percent	700
ASTM C 719	Joint Movement Capability	percent	±50
ASTM D 624	Tear Strength, die B	kg/cm	11

1. ASTM – American Society for Testing and Materials.
2. Based on South Coast Air Quality Management District of California. Maximum VOC is listed both inclusive and exclusive of water and exempt compounds.

Description	DOWSIL 789 Silicone Weatherproofing Sealant is a one-part, neutral- cure, architectural grade sealant. It easily extrudes in any weather and cures at ambient temperature by reaction with moisture in the air to form a durable, flexible silicone rubber seal.
How To Use	<p>Please consult the technical manual. Please contact your local sales application engineer for specific advice.</p> <p><b>Preparation</b> Clean all joints, removing all foreign matter and contaminants such as grease, oil, dust, water, frost, surface dirt, old sealants or glazing compounds and protective coatings.</p> <p><b>Application Method</b> Install backing material or joint filler, setting blocks, spacer shims and tapes. Mask areas adjacent to joints to ensure neat sealant lines. Primer is generally not required on non-porous surfaces, but maybe necessary for optimal sealant of certain porous surfaces. A test placement is always recommended. Apply DOWSIL 789 Silicone Weatherproofing Sealant in a continuous operation using a positive pressure. (The sealant can be applied using many types of air-operated guns and most types of bulk dispensing equipment.) Before a skin forms (typically within 15-20 minutes), tool the sealant with light pressure to spread the sealant against backing material and the joint surfaces. Remove masking tape as soon as the bead is tooled.</p>
Approvals/ Specifications	<p>Meets the requirements of: KS F 4910-2000 F25LM</p> <p><b>Colors</b> This product is available in 6 colors: black, gray, bronze, limestone, precast white and white. Custom colors may be ordered to match virtually any substrate.</p>
Handling Precautions	PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT <a href="http://WWW.CONSUMER.DOW.COM">WWW.CONSUMER.DOW.COM</a> , OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.
Usable Life And Storage	When stored at or below 30°C (86°F) in the original unopened containers, DOWSIL 789 Silicone Weatherproofing Sealant has a usable life of 12 months from the date of manufacture. Refer to product packaging for "Use By" date.
Packaging Information	This product is available in 300 ml disposable cartridges and in 500 ml foil sausages depending on location of purchase.

## Limitations

DOWSIL 789 Silicone Weatherproofing Sealant is not approved for use as a structural sealant.

DOWSIL 789 Silicone Weatherproofing Sealant should not be used:

- In below-grade applications
- When surface temperatures exceed 50°C (122°F)
- On surfaces that are continuously immersed in water
- On building materials that bleed oils, plasticizers or solvents, green or partially vulcanized rubber gaskets or tapes
- On frost-laden or wet surfaces
- In totally confined joints (the sealant requires atmospheric moisture for cure)
- If the sealant is intended to be painted (paints do not typically adhere to most silicone sealants)
- To surfaces in direct contact with food or other food-grade applications

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [www.consumer.dow.com](http://www.consumer.dow.com) or consult your local Dow representative.

<http://www.consumer.dow.com>

### LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

A 10-year Weatherseal Limited Warranty is available. Some testing may be required. Consult your Dow sales application engineer for details.

