

Low-Shrink™ OP-67-LS Precision Positioning Optical Adhesive

APPLICATIONS

- Optic/Lens Alignment
- VCSEL Positioning
- Prism Placement

FEATURES

- UV/Visible Light Cure
- Complete Cure in Seconds
- Minimal Shrinkage During Cure
- Low CTE for Stability Through Thermal Excursions
- Low VOC

OTHER FEATURES

- Low Moisture Absorption
- Adhesion to Various Substrates Including Acrylic and Other Plastics
- Low Outgassing

Dymax Low-Shrink™ OP-67-LS cures upon exposure to light and is designed for rapid positioning of optical components. Low-Shrink™ is a patented technology designed to minimize movement of high-accuracy optical components during cure and throughout service life. Dymax Low-Shrink™ materials contain no nonreactive solvents and cure upon exposure to light. Their ability to cure in seconds enables faster processing, greater output, and lower processing costs. When cured with Dymax light-curing spot lamps, focused-beam lamps, or flood lamps, they deliver optimum speed and performance for optical assembly. Dymax lamps offer the optimum balance of UV and visible light for the fastest, deepest cures. This product is in full compliance with the RoHS Directives 2002/95/EC and 2003/11/EC.

UNCURED PROPERTIES *

| Property | Value | Test Method |
|------------------------|-------------------------|-------------|
| Solvent Content | No Nonreactive Solvents | N/A |
| Chemical Class | Acrylated Urethane | N/A |
| Appearance | White Paste | N/A |
| Soluble in | Organic Solvents | N/A |
| Density, g/ml | 1.14 g/ml | ASTM D1875 |
| Viscosity, cP (20 rpm) | 135,000 (nominal) | ASTM D2556 |

ADHESION

| Substrate | Recommendation |
|-----------|----------------|
| Ceramic | ✓ |
| Glass | ✓ |
| Metal | ✓ |
| Plastic | ✓ |

✓ Recommended o Limited Applications
st Requires Surface Treatment (e.g. plasma, corona treatment, etc.)

CURED MECHANICAL PROPERTIES *

| Property | Value | Test Method |
|---------------------------------------------------|--------------|-------------|
| Durometer Hardness | D80 | ASTM D2240 |
| Tensile at Break, MPa [psi] | 28 [4,000] | ASTM D638 |
| Elongation at Break, % | 6.5 | ASTM D638 |
| Modulus of Elasticity, MPa [psi] | 570 [83,000] | ASTM D638 |
| Glass Transition T_g , °C | 86 | DSTM 256† |
| CTE $_{\alpha 1}$, $\mu\text{m/m}^\circ\text{C}$ | 84 | DSTM 610† |
| CTE $_{\alpha 2}$, $\mu\text{m/m}^\circ\text{C}$ | 180 | DSTM 610† |

OTHER CURED PROPERTIES *

| Property | Value | Test Method |
|-----------------------------------|-------|-------------|
| Refractive Index (20° C) | N/A | ASTM D542 |
| Boiling Water Absorption, % (2 h) | 2.9 | ASTM D570 |
| Water Absorption, % (25° C, 24 h) | 2.3 | ASTM D570 |
| Linear Shrinkage, % | 0.08 | ASTM D2566 |

* Not Specifications

N/A Not Applicable

‡ DSTM Refers to Dymax Standard Test Method



© 2008-2013 Dymax Corporation. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A.

Technical data provided is of a general nature and is based on laboratory test conditions. Dymax does not warrant the data contained in this bulletin. Any warranty applicable to the product, its application and use is strictly limited to that contained in Dymax standard Conditions of Sale. Dymax does not assume responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this communication shall act as a representation that the product use or application will not infringe on a patent owned by someone other than Dymax or act as a grant of license under any Dymax Corporation Patent. Dymax recommends that each user adequately test its proposed use and application before actual repetitive use, using the data in this communication as a general guideline.

Technical Data Collection Prior to 2008

Rev. 04/23/2013

Dymax Corporation
860.482.1010
info@dymax.com
www.dymax.com

Dymax Oligomers & Coatings
860.626.7006
oligomers&coatings@dymax.com
www.dymax-oc.com

Dymax Europe GmbH
+49 (0) 611.962.7900
info_de@dymax.com
www.dymax.de

Dymax UV Adhesives & Equipment (Shenzhen) Co Ltd
+86.755.83485759
dymaxasia@dymax.com
www.dymax.com.cn

Dymax UV Adhesives & Equipment (Shanghai) Co Ltd
+86.21.37285759
dymaxasia@dymax.com
www.dymax.com.cn

Dymax Asia (H.K.) Limited
+852.2460.7038
dymaxasia@dymax.com
www.dymax.com.cn

Dymax Korea LLC
82.2.784.3434
info@dymax.kr
www.dymax.co.kr

CURING GUIDELINES

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm² [10 psi] between glass slides. Actual cure time typically is 3 to 5 times fixture time.

| Dymax Curing System (Intensity) | Fixture Time or Belt Speed ^A |
|-----------------------------------------------------------------------|-----------------------------------------|
| 2000-EC (50 mW/cm ²) ^B | <1 s |
| 5000-EC (200 mW/cm ²) ^B | <1 s |
| BlueWave [®] 75 (5.0 W/cm ²) ^B | <0.2 s |
| BlueWave [®] 200 (10 W/cm ²) ^B | >0.2 s |
| UVCS Conveyor with one 5000-EC (200 mW/cm ²) ^C | >8.2 m/min [>27 ft/min] |
| UVCS Conveyor with Fusion F300S (2.5 W/cm ²) ^C | >8.2 m/min [>27 ft/min] |

A Curing through light-blocking substrates may require longer cure times if they obstruct wavelengths used for light curing (320-400 nm for UV light curing, 320-450 nm for UV/Visible light curing). These fixture times/belt speeds are typical for curing thin films through 100% light-transmitting substrates.

B Intensity was measured over the UVA range (320-395 nm) using a Dymax ACCU-CAL[™] 50 Radiometer.



C At 53 mm [2.1 in] focal distance. Maximum speed of conveyor is 8.2 m/min [27 ft/min]. Intensity was measured over the UVA range (320-395 nm) using the Dymax ACCU-CAL[™] 100 Radiometer.

Full cure is best determined empirically by curing at different times and intensities, and measuring the corresponding change in cured properties such as tackiness, adhesion, hardness, etc. Full cure is defined as the point at which more light exposure no longer improves cured properties. Higher intensities or longer cures (up to 5x) generally will not degrade Dymax light-curable materials.

Dymax recommends that customers employ a safety factor by curing longer and/or at higher intensities than required for full cure. Although Dymax Application Engineering can provide technical support and assist with process development, each customer ultimately must determine and qualify the appropriate curing parameters required for their unique application.

DEPTH OF CURE

The graphs below show the increase in depth of cure as a function of exposure time with two different lamps at different intensities. A 9.5 mm [0.37 in] diameter specimen was cured in a polypropylene mold and cooled to room temperature. It was then released from the mold and the cure depth was measured.



OPTIMIZING PERFORMANCE AND HANDLING

1. This product cures with exposure to UV and visible light. Exposure to ambient and artificial light should be kept to a minimum before curing. Dispensing components including needles and fluid lines should be 100% light blocking, not just UV blocking.
2. All surfaces in contact with the material should be clean and free from flux residue, grease, mold release, or other contaminants prior to dispensing the material.
3. Cure speed is dependent upon many variables, including lamp intensity, distance from the light source, required depth of cure, thickness, and percent light transmission of components between the material and light source.
4. Oxygen in the atmosphere may inhibit surface cure. Surfaces exposed to air may require high-intensity ($>100 \text{ mW/cm}^2$) UV light to produce a dry surface cure. Flooding the curing area with an inert gas, such as nitrogen, can also reduce the effects of oxygen inhibition.
5. Parts should be allowed to cool after cure before testing and subjecting to any loads or electrical testing.
6. In rare cases, stress cracking may occur in assembled parts. Three options may be explored to eliminate this problem. One option is to heat anneal the parts to remove molded-in stresses. A second option is to open any gap between mating parts to reduce stress caused by an interference fit. The third option is to minimize the amount of time the liquid material remains in contact with the substrate(s) prior to curing.
7. Light curing generally produces some heat. If necessary, cooling fans can be placed in the curing area to reduce the heating effect on components.
8. At the point of curing, an air exhaust system is recommended to dissipate any heat and vapors formed during the curing process.

DISPENSING THE MATERIAL

This material may be dispensed with a variety of manual and automatic applicators or other equipment as required. Questions relating to dispensing and curing systems for specific applications should be referred to Dymax Application Engineering.

CLEAN UP

Uncured material may be removed from dispensing components and parts with organic solvents. Cured material will be impervious to many solvents and difficult to remove. Clean up of cured material may require mechanical methods of removal.

PERFORMANCE AFTER TEMPERATURE EXPOSURE

Dymax light-curable materials typically have a lower thermal limit of -54°C [-65°F] and an upper limit of 150°C [300°F]. Many Dymax products can withstand temperatures outside of this range for short periods of time. Please contact Dymax Application Engineering for assistance.

STORAGE AND SHELF LIFE

Store the material in a cool, dark place when not in use. Do not expose to light. This product may polymerize upon prolonged exposure to ambient and artificial light. Keep covered when not in use. This material has a six-month shelf life from date of shipment, unless otherwise specified, when stored between 10°C [50°F] and 32°C [90°F] in the original, unopened container.

GENERAL INFORMATION

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from skin with soap and water. Never use organic solvents to remove material from skin and eyes. For more information on the safe handling of this material, please refer to the Material Safety Data Sheet before use.

RECOMMENDED DYMAX LITERATURE

| | |
|---------|---------------------------------------------------------|
| LIT010A | Guide to Selecting and Using UV Light-Curing Systems |
| LIT077 | Chemical Safety |
| LIT133 | UV Light-Curing System Safety Considerations |
| LIT159 | ACCU-CAL™ 50 Radiometer |
| LIT206 | Flood and Focused-Beam UV Light-Curing Systems |
| LIT208 | UV Light-Curable Lens Bonding and Fiber Optic Adhesives |
| LIT218 | BlueWave® 200 UV Light-Curing Spot Lamp |

Literature is available through our website, www.dymax.com, or by calling any Dymax location.