

TEROSON VR 500

Plastilube February 2020

PRODUCT DESCRIPTION

TEROSON VR 500 provides the following characteristics:

Technology	High Quality Grease
Base	Mineral Oils with Bentonite

TEROSON VR 500 is an organophillic, synthetic high quality grease based on super-refined mineral oils and devoid of metallic soap or fatty acid. TEROSON VR 500 exhibits the following characteristics:

Free of metallic soaps

Metallic soaps are not resistant against alkalis. Due to its good pH stability TEROSON VR 500 is resistant against soft alkalis and acids. TEROSON VR 500 is not corrosive.

Flow Behaviour

TEROSON VR 500 has a thixotropic flow behaviour. That means, the grease gets "more thin" and flows easier under kinetic energy. This reaction is reversible, so that the gel character is given immediately after ending the movement. The synthetic thickener of TEROSON VR 500 is stable, it cannot be extruded from lubricating interface areas by sudden shock loads and extreme pressures. This extends lubricant service life and reduces maintenance frequency.

Wash out resistant

TEROSON VR 500 is water-insoluble and has an excellent wash out resistance.

General-purpose versatility

Due to its characteristics mentioned above TEROSON VR 500 can be used for many purposes. TEROSON VR 500 is digestible with every metal and most of the O-Ring materials.

Application Areas:

TEROSON VR 500 has proven advantageous as mounting paste against squeaking of drum and disc brakes. (Please watch instructions of car manufacturers!). Furthermore TEROSON VR 500 is particularly used for heavy duty applications, e.g. mill roll journals, high temperature valve stems, annealing furnace doors, conveyor systems etc. Other applications showing superior savings include machine guides, slides, bearings, enclosed gear boxes, pump compressors, etc. TEROSON VR 500 assures superior pumpability and work stability for long-life lubrication. Being free of entrained air, TEROSON VR 500 is excellent for use in central lubrication systems. TEROSON VR 500 is particularly advantageous because of its easy and convenient processing properties, whenever parts are not easily accessible for TEROSON VR 500 in the tube.

TECHNICAL DATA

(Typical Test Results)

Colour:	brownish
Odour	mild
Consistency:	paste
Density:	approx. 0.9 g/cm ³
Solids:	approx. 9 %
Solids Aerosol	ca. 6 %
Penetration	265 to 295
Drop Point	none
In service temperature:	-45 to 180 °C

PRELIMINARY STATEMENT:

Prior to use it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Application:

Before working with TEROSON VR 500, the aerosol tin has to be shaken well. On account of the sharpened tube at the spray head, TEROSON VR 500 can be sprayed precisely. The optimal distance between the spray head and lubricated part are a few centimetres. If the distance is larger, you will have to expect spraying off target. During work, the spray head has to face upwards. Otherwise there is the danger of just spraying propellant without active substance. Only parts provided by the machine manufacturers' instructions should be sprayed.

Finishing Treatment

TEROSON VR 500 can be wiped well with a scarf or fleece. Deposits can be completely removed with dissolver (e.g. TEROSON VR 10).

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:
Hazards identification
Transport information
Regulatory information

Storage:

Frost sensitive	no
Recommended storage temperature	10 to 20 °C
Shelf life	24 months

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned

herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1